



# **LUCAS** *Coatings & Mastics for the Roofing Trade*

R. M. Lucas Co. 3211 S. Wood St. Chicago, IL 60608 (773) 523-4300 rmlucas.com

## **PRODUCT DATA BULLETIN**

### **#779 ALL-WEATHER FLASHING CEMENT Premium - Wet Surface**

#### **PURPOSE**

Lucas #779 All-Weather Flashing Cement - Wet Surface is an asphalt based roof cement designed for repairing roofs and roof flashings that are wet or under water. This permits repairs immediately and can prevent more extensive water damage.



#### **PRODUCT DESCRIPTION**

All-Weather Flashing Cement - Wet Surface is manufactured from Type I Roofing Asphalt, reinforcing fibers, petroleum solvents and a special additive which displaces moisture and allows application to wet surfaces. This product is equal to our #771 Flashing Cement in both durability and ease of application.

#### **APPLICATION**

The surface to be repaired must be clean and free of debris. Apply #779 All-Weather Flashing Cement evenly with a pointed roofer's trowel or gloved hand. Use sufficient pressure to force water out from underneath the mastic as it is applied. #779 should be applied 1/8 to 1/4 of an inch thick and may be reinforced with glass membrane or polyester fabric to strengthen the repair. Repairs made to wet surfaces should be considered temporary as trapped moisture will expand when heated by the sun causing blisters and potentially new leaks. When making a permanent repair, open up the area and allow it to dry thoroughly. Clean up with Lucas #125 Safe-Solve.

#### **CAUTION**

Combustible mixture, keep away from heat and open flames. Avoid prolonged contact with skin or fumes. If irritation occurs seek medical attention. Do not use near heat or open flame. Keep out of reach of children. Read MSDS prior to use.

## #779 SPECIFICATION

<b>Applicable Specification *</b>	<b>ASTM D 4586 Type I, Asbestos Free</b>
<b>Viscosity</b>	<b>Trowel</b>
<b>Recommended rate of application</b>	<b>1/8 to 1/4 inch thick</b>
<b>Wet Adhesion ASTM D-3409</b>	<b>100%</b>
<b>% Asphalt ASTM D-6511</b>	<b>45 min.</b>
<b>% Solids ASTM D-6511</b>	<b>70 min.</b>
<b>% Non-volatile ASTM D-6511</b>	<b>86 max.</b>
<b>Weight per gallon</b>	<b>8.5 lbs.</b>
<b>Flash Point (TCC)</b>	<b>+100°F (38.7°C)</b>
<b>VOC</b>	<b>Less than 300 g/l</b>
<b>Container Sizes</b>	<b>1, 3, 5, 55 10 oz. tubes</b>



Information contained in this bulletin is offered gratis on the basis of our field experience and laboratory tests conducted carefully using modern equipment verified for accuracy. No warranty is expressed or implied beyond the purchase price of the material. We suggest that the user evaluate the product's suitability for a particular use prior to application. We reserve the right to improve, change, or discontinue specifications and products without prior notice.